



272 Bendix Road, Suite 550
Virginia Beach, VA 23452

PH (757) 498-0186
FX (757) 498-1075



DESCRIPTION	AVERAGE VALUE	UNITS	ASTM METHOD
IZOD Impact	0.212	ft•lb/in width	D256
Water Absorption	6	%	D570
Tensile Strength	1048	psi	D638
Tensile Modulus of Elasticity	64,420	psi	D638
Heat Deflection Temperature Under Load	63.0	°C	D648
Coefficient of Thermal Expansion (Crosswise)	5.12	$\times 10^{-5}$ mm/mm/°C	D696
Coefficient of Thermal Expansion (Widthwise)	6.02	$\times 10^{-5}$ mm/mm/°C	D696
Flexural (Bending) Strength	2,452	psi	D790
Flexural (Bending) Strength (Flexural Modulus of Elasticity)	116,400	psi	D790
Specific Gravity	0.486	N/A	D792
Density	30.2	pcf	D792
Nail Withdrawal Strength	31	lb _f	D1761
Staple Withdrawal Strength	56	lb _f	D1761
Screw Withdrawal Strength	493	lb _f	D1761
Surface Distortion Resistance	136	°F	D3679
Direct Impact Resistance	320	in•lb	D4226